



Beacon Adhesives Co. Inc.

125 So. MacQuesten Pkwy.

Mt. Vernon, NY 10550

www.beaconadhesives.com

Tel: 914-699-3400 Fax: 914-699-2783

Email: david@beaconadhesives.com

Magna-Tac® M677 A/B

UL94 V-0 Compliant, Flame Retardant, Self Leveling, Equal Mix Epoxy Adhesive

	Viscosity (cps) at 77F	Color	Base	Wgt/Gal	Solids	Diluant	Shelf Life
Part A	50,000	Black	Modified	11 lbs.	100 %	Do not	1 year
Part B	50,000	Amber	epoxy	11 lbs.	100 %	dilute	1 year

Magna-Tac M677 is a UL94V-0 compliant, flame retardant, self leveling, high strength, 100% reactive, room temperature curing formulated epoxy adhesive for:

- encapsulating/potting electronic/electrical devices; bonding rigid expanded plastic foams to themselves or to metal, plywood, or other rigid materials.
- bonding a wide variety of skins to cores (expanded polystyrene foam, foamed glass, honeycomb, etc.) in the fabrication of sandwich panels.
- bonding all metals and other rigid materials (such as glass, ceramics, most plastics, plastic foams, structural laminates) to themselves and to each other.

Fully cured bonds attain lap shear strengths in the neighborhood of 3,000 psi when tested at room temperature using ASTM D1002 procedure. Fully cured bonds exhibit minimal shrinkage, are electrical insulators and provide excellent resistance to weather, galvanic action and most chemical, acids and alkalis.

Characteristics

When mixed, Magna-Tac M677 is a high viscous self leveling liquid, making it extremely easy to spread smoothly and evenly. Once it is applied it has about 20-30 minutes open time to mate parts. It is good for bonding dissimilar substrates and void-filling applications.

	Mixing Ratio (by weight)	Properties	Pot Life @ 77° F	Average Lap Shear Strength
Part A Part B	100 PARTS 100 PARTS	Flame Retardant, HighTensile, Self Leveling	45 minutes (60 gms)	2200 psi

Surface Preparation

All bonding surfaces must be thoroughly cleaned, degreased and dried. For plastic surfaces, remove mold release if any.

Preparation of adhesive

Always stir each part thoroughly first. Proportion accurately and mix slowly to avoid entrapping air.

Magna-Tac M677 Part A is colored black; Part B has a natural amber color. Mix equal amounts (by weight or volume) and stir until the color of the mixture is uniform black.

Note: Pot life can be lengthened substantially if shallow mixing vessels are used or smaller batches are mixed. Cover mixed material to prevent water absorption.

Mixed adhesive may be applied with paint roller, brush, etc. Apply enough mixed adhesive to leave about 4-6 mils in the final glue line. This may be accomplished by coating 4-6 mils on one surface only or by coating 2-3 mils on each surface.

If one surface is porous, more adhesive must be applied to fill the voids and yet produce a final glue line thickness of 4-6 mils.



Cure Time

Room Temperature

At room temperature, assemblies can be handled in approximately 2-4 hours. Magna-Tac M677 develops 85% of its maximum strength in 24 hours.

Fast Cure

If a faster cure is required, the following cycles may be used:

Elevated Temperatures

Temperature	Cure Time
150° F	120 minutes
200° F	45 minutes
250° F	30 minutes
300° F	10 minutes

Bonds will continue to improve in strength at room temperature until optimum is reached, usually within 3-4 days.

Properties

Hardness	Shore D 85 ± .02
Volume Resistivity @ 25C ± 3C	Min. 100 x 10 ¹⁴ ohm-cm
Dielectric Constant @ 10 ⁵ cps	2.98 ± .1
Shrinkage Linear, percent	0.7 % Max.

Typical lap shear values obtained when Magna-Tac 777 is used to bond 0.064" etched 2024T3 aluminum alloy to itself in a 1/2 overlap are as follows:

Test Temperature	Tensile Shear, psi
-67 F	2000
77 F	2200
120F	1200
180F	400
200F	200

Container Sizes

50cc dual barrel syringes
400cc dual barrel syringes
1 quart cans
1 gallon cans
5 gallon pails
55 gallon drums

Beacon Adhesives Company

For Ordering & Technical Assistance

Tel: 914-699-3400

Fax: 914-699-2783

www.beaconadhesives.com

The information given and the recommendations made herein are based on our research and believed to be accurate but no guaranty of their accurate is made. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose or any other warranty, express or implied.